

ROTOCHEM 955B

DESCRIPTION

ROTOCHEM 0955B is a specialized blue color plastic compound designed for rotational molding applications. It is a compound of linear medium density polyethylene copolymer grade with a narrow molecular weight distribution with TiO_2 that possesses a range of beneficial characteristics. ROTOCHEM is an ideal choice for manufacturers who require a reliable and durable material that can withstand harsh environmental conditions. Whether utilized in industrial or consumer applications, this plastic material is a suitable choice for those seeking consistent and stable materials.

Property	Test Method	Unit	Typical Value
MFI (190°C /2.16 kg)	ASTM D 1238-7	(g/10min)	3.5 ± 0.5
Density (23°C)	ASTM D1505-68	(kg/m ³)	0.937-0.945
Pigment content	-	%	0.3-0.5
Moisture content	ASTM D6980-17	(ppm)	≤ 1500
Vicat softening point	ASTM D1525	MPa	115
Tensile strength @ yield	ASTM D638 - 72	wt. %	15
Elongation @ break	ASTM D638	%	> 700
Flexural modulus	ASTM D790	MPa	650
Hardness	ASTM D2240	Shore D	65
ESCR (IGEPAL 10%)(F50, 50°C)	ASTM D1693	HR	200

ADVANTAGE

ROTOCHEM 0955B exhibit a number of advantageous features, including excellent dispersion, exceptional impact strength, superior internal and external surface finish, optimal blueness, reliable resistance to stress cracking, and efficient UV stabilization.

PACKAGING

ROTOCHEM 0955B is supplied in powder form packed in 20 kg bags.

STORAGE AND HANDLING

ROTOCHEM 0955B should be stored to prevent direct sunlight and/or heat exposure. The storage area should also be dry and preferably not exceed 50°C; Bad storage conditions may lead to quality deterioration and product performance. It is advisable to process ROTOCHEM within 18 months after delivery.

Disclaimer: The information & data presented herein are typical values & should not be considered specifications and may be used as a guideline only. POLYCHEM does not undertake any responsibility for any outcome or results from adopting or replicating the data mentioned above & information thereon for possible use for various applications. POLYCHEM reserves the right to change the information & data without any prior notice or information. The user will solely be responsible for any process/product usage

